



PETRONAS

# PRODUCT DATA SHEET

MFR 1.0  
Density 920 **ETILINAS LL0209AA**

## Linear Low Density Polyethylene Heavy Duty Film Applications

### DESCRIPTION

**ETILINAS LL0209AA** is a linear low density polyethylene (LLDPE) with butene copolymer, supplied in pellet form, suitable for a wide variety of film applications. It meets the United States Food and Drug Administration (US FDA) criteria for food contact use as specified in 21 CFR 177.1520 (c) 3.1a & 3.2a and Commission Regulation (EU) No. 10/2011.

### CHARACTERISTICS include:

- Easy processing
- Low gels content
- High melt strength
- Good film transparency
- Good mechanical properties
- No slip/antiblock additives

### APPLICATIONS include:

- Food packaging
- Industrial packaging and garment bags
- Shopping bags

Product Properties*	Test Method	Units	Value
<b>General Properties</b>			
Melt Flow Rate, I <sub>2</sub>	ASTM D 1238 @ 190°C, 2.16kg	g/10min	1.0
Nominal Density	ASTM D 1505	kg/m <sup>3</sup>	920
Melting Point	ISO 3146	°C	122
Vicat Softening Temperature	ASTM D 1525, Load: 1 kg; Heating rate: 50°C/hr	°C	100
<b>Mechanical Properties</b>			
Tensile Strength at Yield, (MD/TD)	ISO 527-3	MPa	11/12
Tensile Strength at Break, (MD/TD)	ISO 527-3	MPa	40/31
Elongation at Break, (MD/TD)	ISO 527-3	%	1540/1560
Elmendorf Tear Strength, (MD/TD)	ISO 6383/2	g/25µm	160/400
Dart Impact Strength	ISO 7765-1, (A)	g	160
<b>Other Properties</b>			
Clarity	ASTM D 1746	%	90
Gloss (45°)	ASTM D 2457	GU	52
Haze	ASTM D 1003	%	30

\*The physical properties shown are typical values obtained by averaging a number of test results and small divergence from quoted figures may occur.

Film properties are typical blown film of 38 microns extruded at Blow Up Ratio (BUR) 2:1

## Typical Processing Conditions

Processing temperature of **ETILINAS LL0209AA** is in the range of 170°C to 210°C depending on the production throughput.

# PRODUCT DATA SHEET



PETRONAS

MFR 1.0  
Density 920 **ETILINAS LL0209AA**

## Linear Low Density Polyethylene Heavy Duty Film Applications

### REGULATORY

**ETILINAS LL0209AA** complies with the following specification when processed using good extrusion practice:-

- US FDA Regulation 21 CFR 177.1520 and CFR 178.2010.
- Commission Regulation (EU) No. 10/2011.
- HALAL certified.
- REACH, RoHS and SVHC.

### AVAILABILITY

**ETILINAS LL0209AA** are available in 25kg bags. The product grade and batch number are clearly marked on each bag.

### STORAGE/HANDLING

**ETILINAS LL0209AA** should be properly stored in well ventilated environment. Prolonged or improper storage can result in deterioration of product properties. The PETRONAS Chemicals Safety Data Sheet (SDS) contains important safety information and should be viewed before using the product.

### HEALTH & SAFETY

**ETILINAS LL0209AA** is not classified as a dangerous preparation. Please refer to our Safety Data Sheet (SDS) for details on various aspects of safety, recovery and disposal of the product.

### PRODUCT STEWARDSHIP

PETRONAS aims to increase awareness of all the hazards associated with the storage, handling and use of its products. Thoroughly reviewing the accompanying Safety Data Sheets and disseminating the information to all dependent and interested parties is an essential part of any 'Responsible Care' programme.

### RELATED DOCUMENTS

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Safety Data Sheet (SDS)  
Statement on chemicals, regulations and standards  
Statement on compliance to food contact regulations

### FOR MORE INFORMATION

Please contact **PETRONAS Chemicals Group Berhad (PCGB)**, Tower 1, PETRONAS Twin Towers, Kuala Lumpur City Centre, 50088 Kuala Lumpur, Malaysia.

Tel: +(603) 2051 5000 Fax: +(603) 2051 3888 or visit our site [www.petronaschemicals.com](http://www.petronaschemicals.com)

For product queries, kindly email to [polymer.pcg@petronas.com](mailto:polymer.pcg@petronas.com)



CERTIFIED TO ISO 9001:2015  
CERT. NO. : AR1560



### IMPORTANT NOTICE

Information contained in this document is accurate and reliable to the best of the knowledge and belief of PETRONAS Chemicals Group Berhad the suggestions and recommendations offered herein serve as a guide in the use of these material, and cannot be guaranteed because the conditions of use are beyond PCG's control. PCG assumes no responsibility for the use of information supplied, the application, adaption or processing of the products described herein and here by disclaims all liability (except as otherwise provided by the law) in regard to such use.